

AMENDMENTS TO THE SPECIFICATION

Please amend the paragraph bridging pages 36 and 37 as presented below.

F2
Commercially available biodegradable resins were used as the raw materials herein. In this example, the aliphatic polyester type biodegradable resin made by Showa Highpolymer Co., Ltd., and ~~solid~~ sold under the trademark designation of "Bionolle" #1020, including 30% added talc, was used as the talc-containing polybutylene succinate and the polylactic acid type biodegradable resin made by Shimadzu Seisakusho K.K. and sold under the trademark designation of "LACT" #2010 was used as polylactic acid. First, these products in the form of pellets were dried under a reduced pressure at 80°C for four hours. The dried resins were severally processed by the dry blend method using an injection molding device to obtain injection molded slide fasteners, namely the molded fastener A which was formed solely of the talc 30%-containing grade of Bionolle and the molded fastener B which was formed of the talc 30%-containing grade of Bionolle/LACT at a mixing ~~ratio~~ ratio of 80/20 (% by weight) or ~~Bionolle/talc/LACT~~ Bionolle/talc/LACT at a mixing ratio of 56/24/20 (~~% by weight.~~) (% by weight).

FINNEGAN
ENDERSON
FARABOW
GARRETT &
DUNNER LLP

1300 I Street, NW
Washington, DC 20005
202.408.4000
Fax 202.408.4400
www.finnegan.com